Australian Standard®

Non-destructive testing—Ultrasonic testing of fusion welded joints in carbon and low alloy steel



This Australian Standard® was prepared by Committee MT-007, Non-destructive Testing of Metals and Materials. It was approved on behalf of the Council of Standards Australia on 10 May 2007.

This Standard was published on 12 July 2007.

The following are represented on Committee MT-007:

- Australasian Aerospace Non-destructive Testing Committee
- Australian Industry Group
- Australian Institute for Non-Destructive Testing
- ANSTO
- Australian Pipeline Industry Association
- Bureau of Steel Manufacturers of Australia
- Engineers Australia
- National Association of Testing Authorities Australia
- TestSafe Australia
- Victorian WorkCover Authority
- Welding Technology Institute of Australia

This Standard was issued in draft form for comment as DR 06720.

Standards Australia wishes to acknowledge the participation of the expert individuals that contributed to the development of this Standard through their representation on the Committee and through public comment period.

Keeping Standards up-to-date

Australian Standards® are living documents that reflect progress in science, technology and systems. To maintain their currency, all Standards are periodically reviewed, and new editions are published. Between editions, amendments may be issued.

Standards may also be withdrawn. It is important that readers assure themselves they are using a current Standard, which should include any amendments that may have been published since the Standard was published.

Detailed information about Australian Standards, drafts, amendments and new projects can be found by visiting **www.standards.org.au**

Standards Australia welcomes suggestions for improvements, and encourages readers to notify us immediately of any apparent inaccuracies or ambiguities. Contact us via email at **mail@standards.org.au**, or write to Standards Australia, GPO Box 476, Sydney, NSW 2001.

Australian Standard[®]

Non-destructive testing—Ultrasonic testing of fusion welded joints in carbon and low alloy steel

Originated as AS B261.1—1968 and AS B260.1A—1968. Previous edition AS 2207—1994. Fourth edition 2007.

COPYRIGHT

© Standards Australia

All rights are reserved. No part of this work may be reproduced or copied in any form or by any means, electronic or mechanical, including photocopying, without the written permission of the publisher.

Published by Standards Australia GPO Box 476, Sydney, NSW 2001, Australia ISBN 0 7337 8278 7

PREFACE

This Standard was prepared by the Australian members of the Joint Standards Australia/New Zealand Committee MT-007, Non-destructive Testing of Metals and Materials. This Standard supersedes AS 2207—1994, *Non-destructive testing—Ultrasonic testing of fusion welded joints in carbon and low alloy steel.*

After consultation with stakeholders in both countries, Standards Australia and Standards New Zealand decided to develop this Standard as an Australian Standard rather than an Australian/New Zealand Standard.

The objective of this Standard is to specify the qualifications of personnel for nondestructive testing procedures used for ultrasonic testing.

The objective of this edition is to introduce new methods and procedures for ultrasonic testing of fusion welded steels.

The terms 'normative' and 'informative' have been used in this Standard to define the application of the appendix to which they apply. A 'normative' appendix is an integral part of a Standard, whereas an 'informative' appendix is only for information and guidance.

CONTENTS

SECTIO	ON 1 SCOPE AND GENERAL	
1.1	SCOPE	
1.2	REFERENCED DOCUMENTS	4
1.3	DEFINITIONS	
SECTIO	ON 2 FOLUPMENT AND CALIBRATION	
2 1	SCOPE OF SECTION	5
2.1	FOLIPMENT	5
2.2	CALIBRATION OF FOUIPMENT	5
2.3	COUPLANTS	
SECTIO	ON 3 METHODS OF TEST	
3 1	SCOPE AND GENERAL	7
3.2	DESIGNATION OF TEST METHODS AND SURFACE PREPARATION	
5.2	CATEGORIES	7
33	PREPARATION OF TEST SURFACES	
3.4	METHODS FOR SCANNING AND DISCONTINUITY EVALUATION	0 Q
3 5	SENSITIVITY	9
3.6	SIZING OF DISCONTINUITIES	
3.7	OPTIONAL VARIATIONS IN SIZING FOR LEVELS 2, 3 AND 4	
SECTIO	ON 4 OUALIFICATION OF NON-DESTRUCTIVE	
SECTI	TESTING PERSONNEL	
SECTIO	ON 5 PRESENTATION OF TEST DATA	
5 1	GENERAI	21
5.1	RECORD OF TEST	
5.3	TEST REPORT	
APPEN	DICES	
A	PURCHASING GUIDELINES	
В	USE OF REFLECTIVITY DIAGRAMS	
С	FACTORS INFLUENCING PROBE SELECTION	
D	METHODS FOR THE DETERMINATION OF ATTENUATION	
_	AND TRANSFER LOSS	
E	ALTERNATIVE METHODS FOR ESTABLISHING SENSITIVITY	
F	GUIDANCE ON ULTRASONIC TESTING OF WELDS	
G	PROCEDURES FOR SIZING OF DISCONTINUITIES	
Η	GUIDANCE ON THE IDENTIFICATION OF DISCONTINUITIES	
Ι	COMPENSATION FOR CONVEX CURVATURE	

STANDARDS AUSTRALIA

Australian Standard

Non-destructive testing—Ultrasonic testing of fusion welded joints in carbon and low alloy steel

SECTION 1 SCOPE AND GENERAL

1.1 SCOPE

This Standard sets out methods and requirements for the manual ultrasonic testing of full or partial penetration fusion welded joints in carbon and low alloy ferritic steels, 6 mm or greater in thickness, using A-scan presentation and employing four sensitivity levels.

This Standard does not cover the testing of stainless steel.

It does not cover the testing of longitudinal welds when-

- (a) the radius of curvature of fabrications is less than 125 mm; or
- (b) for tubular fabrications having an outside diameter exceeding 250 mm, the ratio of thickness to outside diameter exceeds 0.22.

NOTE: Advice and recommendations on information to be supplied by the purchaser at the time of enquiry or order are contained in the purchasing guidelines set out in Appendix A.

1.2 REFERENCED DOCUMENTS

The following documents are referred to in this Standard:

- AS
- 1101 Graphical symbols for general engineering
- 1101.3 Part 3: Welding and non-destructive examination
- 1171 Non-destructive testing—Magnetic particle testing of ferromagnetic products, components and structures
- 1929 Non-destructive testing—Glossary of terms
- 2083 Calibration blocks and their methods of use in ultrasonic testing
- 2812 Welding, brazing and cutting of metals—Glossary of terms
- 3998 Non-destructive testing—Qualification and certification of personnel

1.3 DEFINITIONS

For the purpose of this Standard, the terms and definitions given in AS 1929 apply. For reference to welding terms, symbols and notation, refer to AS 2812 and AS 1101.3.



The remainder of this document is available for purchase online at

www.saiglobal.com/shop

SAI Global also carries a wide range of publications from a wide variety of Standards Publishers:









BSi



Click on the logos to search the database online.